



Patent Technology Centers

Facsimile Transmission

To:	Name:	Ronald J. Kubovcik (25,401)
	Company:	Kubovcik & Kubovcik
	Fax Number:	703-412-9345
	Voice Phone:	703-412-9494
From:	Name:	Michael J. Feely
	Official Fax Number:	(571) 273-8300
	Official After Final Fax Number:	(571) 273-8300
	Voice Phone:	571-272-1086

37 C.F.R. 1.6 sets forth the types of correspondence that can be communicated to the Patent and Trademark Office via facsimile transmissions. Applicants are advised to use the certificate of facsimile transmission procedures when submitting a reply to a non-final or final Office action by facsimile (37 CFR 1.8(a)).

Fax Notes:

Mr. Kubovcik,

The following is a proposed amendment to put 10/590,442 in condition for allowance. Attached are: a marked-up proposal, a clean proposal, and comments discussing the rationale for these changes. The changes primarily address wording/clarity issues. If acceptable, I will enter these changes in an examiner's amendment.

Sincerely,

Michael J Feely (Primary Examiner; AU 1761)

Date and time of transmission: Friday, May 06, 2011 12:28:06 PM

Number of pages including this cover sheet: 09

Marked-up Version

In the claims:

1. (Proposed Amendment) An epoxy resin composition for carbon-fiber-reinforced composite materials, comprising the following components [A], [B], [C], [D] and [E]:

[A] epoxy resin,
[B] amine curing agent which is dicyandiamide,
[C] phosphorus compound,
[D] curing accelerator which is 1,1'-(4- methyl-m-phenylene)bis(3,3-dimethylurea) and,
[E] [[a]] thermoplastic resin;
wherein the concentration of the component [C] is present in an amount such that the resin composition has a phosphorus atom concentration of 0.2 to 15% by weight in terms of phosphorus atom concentration; and
wherein a content of components [A], [B], [C], [D], and [E] are present in amounts such that the combined amount of components [A], [B], [C], [D], and [E] is at least in the epoxy resin composition is more than 95% by weight, based on the overall resin composition.

2. (Proposed Amendment) The epoxy resin composition for carbon-fiber-reinforced composite materials according to claim 1, characterized in that the wherein the resin composition has a viscosity of the composition is 10 to 700 Pa's at 60°C.

Proposed Amendment for: 10/590,442
(Attorney Docket No. HRK-001)

3. (Proposed Amendment) The epoxy resin composition for carbon-fiber-reinforced composite materials according to claim 1, ~~characterized by comprising red phosphorus as the~~ wherein component [C] comprises red phosphorus.

4. (Proposed Amendment) The epoxy resin composition for carbon-fiber-reinforced composite materials according to claim 3, ~~characterized in that~~ wherein the red phosphorus is coated with a metal hydroxide, a resin or a combination thereof and/or a resin.

5-10. (canceled)

11. (Proposed Amendment) The epoxy resin composition for carbon-fiber-reinforced composite materials according to claim 1, ~~characterized in that~~ wherein the resin composition has a specific gravity of ~~the composition is~~ 1.35 or lower.

12. (Proposed Amendment) The epoxy resin composition for carbon-fiber-reinforced composite materials according to claim 1, ~~characterized in that~~ wherein the resin composition is capable of being cured within 30 minutes at 150°C.

13. (Previously Presented) A prepreg, prepared by impregnating carbon fiber with the epoxy resin composition for carbon-fiber-reinforced composite materials according to claim 1.

Proposed Amendment for: 10/590,442
(Attorney Docket No. HRK-001)

14. (Proposed Amendment) The prepreg according to claim 13, wherein the prepreg has a
characterized in that the fiber volume content of a prepreg is 30 to 95%.

15. (Proposed Amendment) The prepreg according to claim 13, wherein the prepreg is a
woven prepreg or a unidirectional prepreg A fiber reinforced composite sheet,
characterized by comprising a cured resin prepared by curing the epoxy resin
composition for carbon fiber reinforced composite materials according to claim 1; and
carbon fiber.

16. (Proposed Amendment) A fiber-reinforced composite material sheet, prepared by
laminating a plurality of prepgs according to claim 15 and curing said laminate a
prepg according to claim 13.

17-49. (Proposed Cancellation)

50. (New) A fiber-reinforced composite material, prepared by curing the prepreg
according to claim 13.

In the specification:

- Replace the abstract with:
 - The present invention provides a light-weight fiber-reinforced composite material that has excellent flame retardance and mechanical properties and never emits a halogen gas. The present invention also provides a prepreg and [[en]] an epoxy resin composition

Proposed Amendment for: 10/590,442
(Attorney Docket No. HRK-001)

suites to obtain the above described fiber-reinforced composite material. The present invention also provides an integrated molding which is produced using the above described fiber-reinforced composite material, thereby suitable for use in electric/electronic casings. The epoxy resin composition is such that it contains the following components [A], [B], and [C], [D], and [E]:

[A] epoxy resin,

[B] amine curing agent, and

[C] phosphorus compound,

[D] curing accelerator, and

[E] thermoplastic resin,

wherein the resin composition has a phosphorus atom concentration of the component [C] is 0.2 to 15% by weight in terms of phosphorus atom concentration--

Clean Version

In the claims:

1. (Proposed Amendment) An epoxy resin composition for carbon-fiber-reinforced composite materials, comprising the following components [A], [B], [C], [D] and [E]:

[A] epoxy resin,
[B] amine curing agent which is dicyandiamide,
[C] phosphorus compound,
[D] curing accelerator which is 1,1'-(4- methyl-m-phenylene)bis(3,3-dimethylurea) and,
[E] thermoplastic resin;
wherein component [C] is present in an amount such that the resin composition has a phosphorus atom concentration of 0.2 to 15% by weight; and
wherein components [A], [B], [C], [D], and [E] are present in amounts such that the combined amount of components [A], [B], [C], [D], and [E] is at least 95% by weight, based on the overall resin composition.

2. (Proposed Amendment) The epoxy resin composition for carbon-fiber-reinforced composite materials according to claim 1, wherein the resin composition has a viscosity of 10 to 700 Pa's at 60°C.

3. (Proposed Amendment) The epoxy resin composition for carbon-fiber-reinforced composite materials according to claim 1, wherein component [C] comprises red phosphorus.

4. (Proposed Amendment) The epoxy resin composition for carbon-fiber-reinforced composite materials according to claim 3, wherein the red phosphorus is coated with a metal hydroxide, a resin or a combination thereof.

5-10. (canceled)

11. (Proposed Amendment) The epoxy resin composition for carbon-fiber-reinforced composite materials according to claim 1, wherein the resin composition has a specific gravity of 1.35 or lower.

12. (Proposed Amendment) The epoxy resin composition for carbon-fiber-reinforced composite materials according to claim 1, wherein the resin composition is capable of being cured within 30 minutes at 150°C.

13. (Previously Presented) A prepreg, prepared by impregnating carbon fiber with the epoxy resin composition for carbon-fiber-reinforced composite materials according to claim 1.

14. (Proposed Amendment) The prepreg according to claim 13, wherein the prepreg has a fiber volume content of 30 to 95%.

15. (Proposed Amendment) The prepreg according to claim 13, wherein the prepreg is a woven prepreg or a unidirectional prepreg.

16. (Proposed Amendment) A fiber-reinforced composite material, prepared by laminating a plurality of prepgs according to claim 15 and curing said laminate.

17-49. (Proposed Cancellation)

50. (New) A fiber-reinforced composite material, prepared by curing the prepreg according to claim 13.

In the specification:

- Replace the abstract with:

-- The present invention provides a light-weight fiber-reinforced composite material that has excellent flame retardance and mechanical properties and never emits a halogen gas. The present invention also provides a prepreg and an epoxy resin composition suited to obtain the above described fiber-reinforced composite material. The present invention also provides an integrated molding which is produced using the above described fiber-reinforced composite material, thereby suitable for use in electric/electronic casings. The epoxy resin composition is such that it contains the following components [A], [B], [C], [D], and [E]: [A] epoxy resin, [B] amine curing agent, [C] phosphorus compound, [D] curing accelerator, and [E] thermoplastic resin, wherein the resin composition has a phosphorus atom concentration of 0.2 to 15% by weight.--

Comments

- In claim 1, the phosphorus content limitation was amended to improve clarity.
Paragraph 0070 of the corresponding pre-publication was used for guidance.
- In claim 1, the [A-E] content limitation was amended to improve clarity.
0099
Paragraph 0090 of the corresponding pre-publication was used for guidance.
- Claims 2-4, 11, 12, and 14 were amended to address minor wording issues. The changed were made to improve clarity.
- Claim 15 was amended to feature the preprep limitations discussed in paragraphs 0107-0108 of the corresponding pre-publication.
- Claim 16 was amended to feature the composite material discussed in paragraphs 0107-0108 of the corresponding pre-publication.
- Claims 17-49 were cancelled because they were withdrawn without traverse.
- Claim 50 was added to feature the composite material discussed in paragraph 0115 of the corresponding pre-publication.
- The abstract was amended into a single-paragraph. It also better reflects the claimed subject matter.